


Metal Test Ltd



P O Box 12633
Penrose
Auckland 1642
NEW ZEALAND

Phone: 64-9-525 0332
Fax: 64-9-525 1873
A/H: 64-9-235 9083
Mobile: 0274 394 545
Email: clive@metaltest.co.nz

Laboratory: 172G Marua Road, Mt Wellington, Auckland 1051

** EMAIL FORMAT **

30 September 2008

Masons Limited
P O Box 300771
Albany
NORTH SHORE CITY

ATTENTION: Mr Trent Mason

TEST CERTIFICATE	
Job No. J9243	Order No. None given
Three galvanised brick ties were submitted for determination of the coating mass / metre ² . These samples were tested in accordance with AS2331-2-1 using Reagent 7.	
RESULTS	
Total surface area was 6636.82 mm ² x three samples = 19910.5 mm²	
Weight before test = 92.72 g Weight after test = 82.42 g = 10.30 g loss	
Therefore coating mass = $\frac{10.30 \text{ g}}{19910.5 \text{ mm}^2}$ = 517 g / m²	
Coating mass was 517 g/m ² which conforms to the requirements of NZS3604-1999 galvanised to AS/NZS2699.1 which states 470 g /m ² minimum on galvanised wall ties.	
<i>Clive Jennings</i>	
Signed:	CLIVE JENNINGS